

QUALITA EN 10025	TENSIONE DI SNERVAMENTO	TENSIONE DI ROTTURA		RESILIENZA	
		(ReH N/mm2 min)	(Rm N/mm2)	(Rm N/mm2)	
		Spessore < 3 mm	Spessore > 3 mm	Temp. °C	J
S235JR	235	360 – 510	340 – 470	20	27
S275JR	275	430 – 580	410 – 560	20	27
S275J0	275	430 – 580	410 – 560	0	27
S355JR	355	510 – 680	490 – 630	20	27
S355J20	355	510 – 680	490 – 630	0	27
S355J2+N	355	510 – 680	490 – 630	-20	27