

NORMA	TENSIONE DI ROTTURA			TENSIONE DI SNERVAMENTO			IMPACT EN.		
	Rm (Mpa)			ReH (Mpa)			KV (J)		
Sp,(mm)	3 – 50	50 – 100	100 – 150	3 – 50	50 – 100	100 – 150	0°C	-20°C	-40°C
S690QL	770-940	760-930	710-900	690	650	630	50	40	30
S690QL1	770-940	760-930	710-900	690	650	630	60	50	40
S890QL	940-1100	880-1100	/	890	830	/	50	40	30
S890QL1	940-1100	880-1100	/	890	830	/	60	50	40