

NAME	Cr %	Mo%	TENSILE (Mpa)	Yield (Mpa)	Sp. Max mm
SA387.11	1.00-1.50	0.45-0.65	515 - 690	310 min	110 mm
SA387.22	2.00-2.50	0.90-1.10	515 - 690	310 min	100 mm
SA387.5	4.00-6.00	0.45-0.65	515 - 690	310 min	60 mm
SA387.91	8.00-9.50	0.85-1.05	585 - 760	415 min	60 mm